



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11) EP 1 069 201 A2

(12) EUROPEAN PATENT APPLICATION

(43) Date of publication:
17.01.2001 Bulletin 2001/03

(51) Int. Cl.⁷: C22C 38/14, C22C 38/32
// C21D1/10

(21) Application number: 00115224.8

(22) Date of filing: 13.07.2000

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 13.07.1999 JP 19883699

(71) Applicant:
DAIDO TOKUSHUKO KABUSHIKI KAISHA
Naka-ku Nagoya-shi Aichi-ken (JP)

(72) Inventors:
• Matsumura, Yasushi,
c/o Daido Tokushuko K.K.
Nagoya-shi, Aichi (JP)

• Kurebayashi, Yutaka,
c/o Daido Tokushuko K.K.
Nagoya-shi, Aichi (JP)
• Nakamura, Sadayuki,
c/o Daido Tokushuko K.K.
Nagoya-shi, Aichi (JP)

(74) Representative:
Diehl, Hermann, Dr. Dipl.-Phys. et al
DIEHL, GLÄSER, HILTL & PARTNER
Patentanwälte
Augustenstrasse 46
80333 München (DE)

(54) Steel for induction hardening

(57) A steel product contains, by mass%, C : 0.45 to 0.60%, Si : 0.01 to 0.15%, Mn : 0.20 to 0.60%, S : 0.012% or lower, Al : 0.015 to 0.040%, Ti : 0.005 to 0.050%, B : 0.0005 to 0.0050%, N : 0.010% or lower, O : 0.0010% or lower, and balance being Fe and unavoidable impurities. Limitations are provided to allowable maximum sizes per each sort of contained non-metallic inclusions and the number per unit area thereof. This steel may contains one kind or two kinds or more of Cr: 1.00% or lower, Mo: 0.50% or lower and Ni: 1.50 or lower.

EP 1 069 201 A2

Description

BACKGROUND OF THE INVENTION5 1. Field of the Invention

[0001] The present invention relates to machinery structural parts which are formed by a cold working and are to be produced by strengthening through an induction quenching, the parts being required to have high rolling fatigue strength and torsion fatigue strength, for example, in an outer race for a joint of constant velocity, and a steel for induction quenching to be used thereto.

2. Description of the Related Art

[0002] In general, as machinery structural parts required to have the high fatigue strength such as the outer race for joints of constant velocity, medium carbon steels containing C: 0.40 to 0.60% are used. These steels are formed through a cold forging, and then increased in surface hardness by the induction quenching treatment so as to enhance the rolling fatigue strength and the torsion fatigue strength. These machinery structural parts have recently been demanded for further improving higher strengthening and cold workability because of making light weight.

[0003] Since the medium carbon steel is generally poor in the cold workability, many techniques for improving it have been developed. For example, JP-A-62-23929 and JP-A-62-196327 disclose technologies that Si and Mn in steel are limited, deoxidation and denitrification are carried out by Al and Ti, a fine amount of B is added to guarantee a high hardenability with the amount of small alloying addition, and temperature conditions of hot rolling or finish rolling temperature are controlled for improving the cold workability.

[0004] JP-A-2-129341 discloses a method for improving the cold workability of steel by limiting amounts of Si and Mn, decreasing alloying elements by adding Al, Ti and B as the above two examples, and limiting upper limits of N, S and O.

[0005] On the other hand, enhancing of strength, in particular improvement of fatigue strength mainly depend upon hardening in a skin portion by the induction quenching and compressive residual stress generated thereby, and efforts are directed to adjusting of chemical compositions in steel for efficiently demonstrating effects by the induction quenching. In parts requiring the rolling fatigue strength as outer races for joints of constant velocity, it is desirable that the hardness of the rolling face is high, but if the hardness is enhanced, notch sensibility is increased resulting to invite a lowering of the fatigue strength, and so the enhancing of hardness is limited.

[0006] It is known that, in a hard steel, non-metallic inclusions in steel serve as sources of stress concentration and lowers the fatigue strength of steel. JP-A-2-129341 discloses a method of limiting an upper limit of O content to 0.0020%, taking prevention of deterioration of rolling fatigue life into consideration, and limiting an upper limit of Ti content to 0.05%, paying attention to prevention of forming large nitrides harmful to the rolling fatigue life.

[0007] The fatigue strength may be enhanced to a certain extent by providing methods of adjusting chemical compositions in steel as mentioned above, however, it has been difficult to decrease dispersions of the fatigue strength, in particular dispersions of the rolling fatigue life.

40 SUMMARY OF THE INVENTION

[0008] In view of such circumstances, it is accordingly an object of the invention to provide a steel suited to the induction quenching, having an excellent cold workability, high rolling fatigue strength and torsion fatigue strength, and less dispersions of the fatigue strength as well as machinery structural parts.

[0009] In the steel for the induction quenching, having the excellent cold workability, rolling fatigue strength and torsion fatigue strength and the machinery structural parts, mainly the contents of Si and Mn are limited for enhancing the cold workability, and B is added at a proper content for compensating the lowering of induction hardenability. For enhancing the effect of the B addition, the contents of O and N are limited, and Al and Ti of appropriate contents are added for carrying out deoxidation and denitrification. Cr, Ni and Mo may be added at small contents for compensating the hardenability of steel and increasing toughness of the same. Further, if decreasing contents of S, O and N forming non-metallic inclusions, and controlling sizes of formed non-metallic inclusions, the fatigue strength of the induction-quenched steel is improved and the dispersion thereof are lowered.

[0010] According to the present invention, the steel for high frequency induction quenching having excellent cold workability, rolling fatigue strength and torsion fatigue strength

(1) contains by mass%

C : 0.45 to 0.60%,
 Si : 0.01 to 0.15%,
 Mn : 0.20 to 0.60%,
 S : 0.012% or lower,
 Al : 0.015 to 0.040%,
 Ti : 0.005 to 0.050%,
 B : 0.0005 to 0.0050%,
 N : 0.010% or lower,
 O : 0.0010% or lower, and
 balance being Fe and unavoidable impurities,

wherein preferably maximum sizes of contained non-metallic inclusions are, in terms of equivalent circular diameters, 15 μm or less in oxide based non-metallic inclusions, 5 μm or less preferably 4.5 μm or less in nitride based non-metallic inclusions, and 15 μm or less in sulfide based non-metallic inclusions respectively, and the numbers of the non-metallic inclusions of the equivalent circular diameters being 1 μm or more are 6 or less preferably 5 or less per 1 mm^2 in the oxide based inclusions, 10 or less per 1 mm^2 in the nitride based non-metallic inclusions, and 5 or less per 1 mm^2 in the sulfide based non-metallic inclusions.

(2) The steel further contains, in addition to (1), at least one of

Cr : 1.00% or lower,
 Mo : 0.50% or lower, and
 Ni : 1.50% or lower.

The inventive machinery structural parts have the excellent cold workability, rolling fatigue strength and torsion fatigue strength:

(3) comprises the steel for high frequency induction quenching as set forth in any one of (1) and (2).

DETAILED DESCRIPTION OF THE INVENTION

[0011] Further reference will be made to reasons for limiting the containing percentage of the chemical composition in the steel for induction quenching, having the excellent cold workability, rolling fatigue strength and torsion fatigue strength.

C: 0.45 to 0.60%

[0012] C is a necessary element for raising the quenched hardness and securing the strength of the machinery structural parts. It is therefore necessary to contain C at least 0.45%. But if excessively containing, since the cold workability and machinability are spoiled and quenching cracks might be caused when the induction quenching is performed, the upper limit of C is determined to be 0.60%.

Si: 0.01 to 0.15%

[0013] Si is added as a deoxidizing agent when melting a steel, and for exhibiting the addition effect, Si should be added at least 0.01%. But if the content is as an ordinary deoxidizing agent, it deteriorates the cold workability of steel, and for enhancing the cold workability, the upper limit is determined to be 0.15%. Preferably, Si is contained in the range of 0.05 to 0.10%.

Mn: 0.20 to 0.60%

[0014] Mn serves as a deoxidizing agent when melting a steel and enhances a hardenability of steel. For exhibiting these effects, Mn should be added at least 0.20%. But if excessively containing, since the cold workability and machinability are spoiled, the upper limit of Mn is set to be 0.60%. Preferably, Mn is contained in the range of 0.20 to 0.50%.

S: 0.012% or lower

[0015] S forms sulfide based non-metallic inclusions (JIS: A1 based inclusions) in steel and damages the cold workability and decreases the fatigue strength. So the less, the more desirable, but if it is too low, since the machinability

decreases, S may be contained in the range of 0.012% or lower. Preferably, S is contained in the range of 0.010% or lower.

Al: 0.015 to 0.040%

5

[0016] Al is a strong deoxidizing element and prevents crystal grain of steel from coarsening. For obtaining these effects, Al of 0.015% or higher is contained. But since Al forms Al_2O_3 as one of oxide based non-metallic inclusions and injures the fatigue strength of steel, the upper limit of Al is set to be 0.040%. Preferably, Al is contained in the range of 0.020% to 0.035%.

10

Ti: 0.005 to 0.050%

[0017] Ti of 0.005% or higher is added for improving the hardenability of steel provided by B. But since Ti forms the nitride based non-metallic inclusions and spoils the fatigue strength, the upper limit is set to be 0.050%. Preferably, Ti is contained in the range of 0.020% to 0.035%.

15

B: 0.0005 to 0.0050%

[0018] B is added to compensate the deterioration of the hardenability by lowering the contents of Si and Mn and to secure a desired depth of hardening. It is accordingly necessary to contain 0.0005% or higher. But an excessive addition coarsens crystal grain of steel and harms a toughness, so the upper limit is set to be 0.0050%. Preferably, B is contained in the range of 0.0010 to 0.0030%.

20

N: 0.010% or lower

25

[0019] N forms nitride based non-metallic inclusions (JIS: C2 based inclusions) in steel to and injures the fatigue strength, and therefore the upper limit is 0.010%.

O: 0.0010% or lower

30

[0020] O forms oxide based non-metallic inclusions (JIS: C1 based inclusions) in steel and injures the fatigue strength, and the upper limit is 0.0010%.

Cr: 1.00% or lower

35

[0021] Cr may be added for compensating the hardenability of steel. But since an excessive content spoils the cold workability and it is difficult to make carbides in the induction quenching solid, the upper limit of Cr is set to be 1.00%. Preferably, Cr is contained in the range of 0.50% or lower.

40

Mo: 0.50% or lower

[0022] Mo enhances the hardenability of steel, strengthens a grain boundary and raises a toughness of martensite, and so its addition is permitted, but since an excessively content deteriorates the cold workability and machinability, the upper limit is set to be 0.50%. Preferably, Mo is contained in the range of 0.40% or lower.

45

Ni: 1.50% or lower

[0023] Ni enhances the hardenability of steel and raises the toughness of martensite, and so its addition is permitted, but if excessively containing, since it spoils the cold workability and the machinability of steel, the upper limit is to be 1.50%. Preferably, Ni is contained in the range of 1.20% or lower.

50

[0024] With respect to the induction quenching steel of the invention, for enhancing the fatigue strength of steel, in response to sorts of non-metallic inclusions, there are provided limitations on a maximum size of non-metallic inclusions and a distributed density of non-metallic inclusions having sizes larger than predetermined size. Non-metallic inclusions are tested in accordance with JIS G 0555 (microscopic testing method of non-metallic inclusions of steel), and sorts are divided of non-metallic inclusions observed on faces to be tested, while equivalent circular diameters and the number thereof are measured. The "equivalent circular diameter" herein is defined by a diameter of a circle having an equal area to the area of the non-metallic inclusion observed on the face to be tested.

55

[0025] The induction quenching steel of the invention is formed into a shape of the machinery structural part, and

then subjected to a hardening heat treatment as the induction quenching to provide a high strength available for usage.

[0026] According to results of many tests, in order to realize the high strength steel having the high fatigue strength with less distribution of the fatigue strength, it is necessary that maximum sizes of contained non-metallic inclusions are, in terms of equivalent circular diameters, 15 μm or less in oxide based non-metallic inclusions, 5 μm or less in nitride based non-metallic inclusions, and 15 μm or less in sulfide based non-metallic inclusions respectively, and the numbers of the non-metallic inclusions of the equivalent circular diameters being 1 μm or more are 6 or less per 1 mm^2 in the oxide based inclusions, 10 or less per 1 mm^2 in the nitride based non-metallic inclusions, and 5 or less per 1 mm^2 in the sulfide based non-metallic inclusions.

[0027] If using the steel containing the above mentioned chemical composition and having properties of the non-metallic inclusions, it is possible to efficiently carry out the process high in dimensional precision by the cold workings such as the cold forging or cold extrusion, and to obtain the machinery structural parts high in the rolling fatigue strength and the torsion fatigue strength by dealing with the hardening heat treatment such as the induction quenching.

Examples

[0028] Steels shown in Table 1 were melted in an arc furnace of 70 ton, vacuum-degassified (degree of vacuum: 1 torr or less and the holding time: 15 minutes or longer), and continuously cast into blooms of 370 mm x 500 mm in cross sectional dimension. Al and Ti were added after 3 minutes passed after the vacuum degassification treatment. The bloom materials were hot-rolled into bar steels of 80 mm diameter and 55 mm diameter, and normalized 900°C x 60 min in an air. Some of the bar steels were subjected to the heating of 750°C x 8 hr, followed by spheroidizing annealings of 10°C/1 hr.

Table 1-a

	Chemical composition (mass %)												Remarks (Note) nd: Not detected
	C	Si	Mn	S	Al	Ti	B	N	O	Ni	Cr	Mo	
Example 1	0.46	0.08	0.28	0.010	0.021	0.035	0.0014	0.008	0.0008	0.08	0.15	nd	
Example 2	0.46	0.06	0.35	0.009	0.022	0.038	0.0012	0.007	0.0009	0.07	0.16	nd	
Example 3	0.47	0.07	0.42	0.005	0.028	0.038	0.0015	0.009	0.0008	0.08	0.15	nd	
Example 4	0.46	0.09	0.22	0.010	0.025	0.036	0.0011	0.009	0.0010	0.05	0.43	nd	
Example 5	0.47	0.09	0.31	0.009	0.028	0.036	0.0011	0.008	0.0009	0.06	0.14	0.28	
Example 6	0.48	0.07	0.23	0.010	0.031	0.030	0.0014	0.007	0.0009	1.05	0.17	nd	
Example 7	0.52	0.09	0.28	0.006	0.033	0.038	0.0013	0.009	0.0008	0.07	0.18	nd	
Example 8	0.53	0.08	0.31	0.010	0.029	0.039	0.0015	0.008	0.0010	0.04	0.21	nd	
Example 9	0.54	0.09	0.41	0.010	0.031	0.035	0.0015	0.009	0.0010	0.08	0.18	nd	
Example 10	0.52	0.07	0.21	0.007	0.029	0.032	0.0012	0.007	0.0007	0.09	0.42	nd	
Example 11	0.52	0.07	0.24	0.011	0.028	0.032	0.0012	0.007	0.0009	0.05	0.13	0.20	
Example 12	0.53	0.08	0.28	0.010	0.026	0.034	0.0015	0.008	0.0010	1.18	0.18	nd	
Example 13	0.57	0.08	0.24	0.009	0.027	0.034	0.0012	0.006	0.0009	0.07	0.13	nd	
Example 14	0.56	0.07	0.30	0.009	0.028	0.025	0.0011	0.007	0.0009	0.07	0.17	nd	
Example 15	0.57	0.09	0.41	0.010	0.029	0.036	0.0014	0.008	0.0010	0.08	0.15	nd	

Table 1-b

	Chemical composition (mass %)												Remarks
	C	Si	Mn	S	Al	Ti	B	N	O	Ni	Cr	Mo	
Comparative example 1	0.41	0.07	0.28	0.011	0.030	0.031	0.0014	0.008	0.0009	0.06	0.15	nd	
Comparative example 2	0.53	0.51	0.45	0.009	0.031	0.038	0.0012	0.008	0.0009	0.09	0.16	nd	
Comparative example 3	0.54	0.07	0.72	0.008	0.028	0.033	0.0013	0.007	0.0010	0.05	0.15	nd	
Comparative example 4	0.49	0.10	0.23	0.010	0.029	0.034	nd	0.008	0.0008	0.06	0.15	nd	
Comparative example 5	0.53	0.08	0.25	0.009	0.031	0.035	nd	0.009	0.0007	0.04	0.02	nd	
Comparative example 6	0.49	0.10	0.54	0.010	0.032	0.034	0.0014	0.008	0.0021	0.03	0.16	nd	
Comparative example 7	0.53	0.09	0.27	0.009	0.031	0.036	0.0012	0.013	0.0009	0.06	0.13	nd	
Comparative example 8	0.54	0.07	0.26	0.007	0.028	0.035	0.0015	0.014	0.0020	0.08	0.14	nd	
Comparative example 9	0.54	0.08	0.27	0.008	0.027	0.051	0.0015	0.006	0.0010	0.09	0.16	nd	
Comparative example 10	0.51	0.08	0.28	0.018	0.030	0.036	0.0014	0.008	0.0008	0.05	0.17	nd	
Comparative example 11	0.54	0.07	0.26	0.006	0.029	0.033	0.0016	0.007	0.0009	0.07	0.15	nd	
Comparative example 12	0.54	0.09	0.27	0.009	0.031	0.039	0.0015	0.007	0.0010	0.06	0.14	nd	
Comparative example 13	0.53	0.07	0.25	0.008	0.012	0.032	0.0015	0.009	0.0009	0.04	0.14	nd	
Comparative example 14	0.64	0.07	0.22	0.009	0.031	0.035	0.0014	0.006	0.0010	0.08	0.13	nd	
Comparative example 15	0.48	0.24	0.75	0.015	0.027	nd	nd	0.013	0.0015	0.05	0.12	nd	JIS S48C-Equivalent steel
Comparative example 16	0.53	0.25	0.76	0.015	0.026	nd	nd	0.012	0.0016	0.06	0.13	nd	JIS S53C-Equivalent steel

[0029] The following measuring and testing were made to the above mentioned normalized materials or the annealed materials. Non-metallic inclusions:

[0030] As to the normalized materials of 55 mm diameter, non-metallic inclusions were detected in accordance with

EP 1 069 201 A2

JIS G 0555 (microscopic testing method of non-metallic inclusions of steel). The observations were made on the actually visual fields of 2 mm^2 . As to the oxide based non-metallic inclusions, the nitride based non-metallic inclusions and the sulfide based non-metallic inclusions, the number of non-metallic inclusions larger than the equivalent circular diameter of $1 \mu\text{m}$ were measured so as to calculate the number of non-metallic inclusion per 1 mm^2 . Of the observed non-metallic inclusions, values of those of the maximum equivalent circular diameter are shown as maximum dimension in Table 2.

10

15

20

25

30

35

40

45

50

55

Table 2-a

	Oxide based Inclusions		Nitride based Inclusions		Sulfide based Inclusions	
	Number (Number/mm ²)	Maximum size (μ m)	Number (Number/mm ²)	Maximum size (μ m)	Number (Number/mm ²)	Maximum size (μ m)
Example 1	1.8	6.0	9.1	2.3	3.8	11.2
Example 2	1.5	7.2	8.5	2.8	4.8	12.3
Example 3	1.6	7.5	7.9	3.1	4.9	13.4
Example 4	1.7	6.1	6.9	2.5	4.5	14.3
Example 5	1.8	8.1	8.1	3.1	3.9	14.0
Example 6	1.4	5.6	9.5	2.2	3.5	12.9
Example 7	1.6	10.1	8.3	3.8	4.9	14.2
Example 8	4.8	9.8	7.2	3.7	4.5	12.9
Example 9	3.2	12.1	8.9	2.9	4.2	13.9
Example 10	4.3	11.1	8.4	4.1	3.9	13.2
Example 11	3.5	13.4	9.6	2.5	4.8	12.1
Example 12	4.8	8.2	7.2	3.4	3.9	11.0
Example 13	3.5	12.4	8.5	3.7	4.6	14.2
Example 14	4.8	13.2	7.9	4.1	4.8	14.9
Example 15	4.7	10.9	7.4	2.8	4.3	12.8

Table 2-b

	Oxide based inclusions		Nitride based inclusions		Sulfide based inclusions	
	Number (Number/mm ²)	Maximum size (μ m)	Number (Number/mm ²)	Maximum size (μ m)	Number (Number/mm ²)	Maximum size (μ m)
Comparative example 1	4.2	12.1	6.9	2.9	4.4	13.1
Comparative example 2	4.1	13.5	8.5	3.1	4.0	14.0
Comparative example 3	3.9	14.2	9.3	3.2	3.8	13.2
Comparative example 4	2.6	13.0	9.1	2.7	4.6	14.8
Comparative example 5	4.2	12.3	7.9	2.7	4.3	13.5
Comparative example 6	3.4	18.2	8.2	2.7	4.5	12.3
Comparative example 7	3.1	11.1	8.9	7.5	3.2	14.6
Comparative example 8	3.1	19.1	8.7	8.3	3.8	13.2
Comparative example 9	3.5	11.2	7.9	3.4	4.5	14.2
Comparative example 10	3.2	12.3	9.1	4.6	3.2	18.2
Comparative example 11	2.3	19.4	8.2	3.1	3.2	14.1
Comparative example 12	3.9	10.1	4.1	9.3	4.3	13.7
Comparative example 13	4.3	12.1	4.0	9.2	4.0	12.3
Comparative example 14	4.9	8.1	9.2	3.8	4.5	13.4
Comparative example 15	4.7	18.2	nd	nd	4.5	14.3
Comparative example 16	4.2	19.3	nd	nd	4.8	13.2

Depth of the hardened layer:

[0031] Test pieces of 25 mm diameter x 80 mm length were cut out from the annealed materials of 55 mm diameter. The induction quenching was performed at the frequency of 10 kHz and for the heating time of 4 seconds in the stationary type, and the depth where the hardness of 450 HV or higher was available was measured. Measured values were made depths of the hardened layers and are shown in Table 3 as parameters of the hardenability.

Deformation resistance

[0032] Test pieces of 6 mm diameter x 12 mm length were cut out around a center axis of D/4 position of the annealed materials of 55 mm diameter, and the compression tests were carried out. Stresses when true strain was 0.8 in the compression test are shown as deformation resistance in Table 3.

Cold workability

[0033] Test pieces of 30 mm diameter x 200 mm length were cut out from the normalized materials of 55 mm diameter. The cold extrusion was performed at the degression of 40% to demand the extrusion number until the abrasion amount of the tool became 0.2 mm. Table 3 shows that the life ratio of the cold worked tool was defined by the value of the ratio when the value obtained in the comparative example 16 (corresponding to JIS S53C) was 1.

Machinability

[0034] Test pieces of 80 mm diameter x 300 mm length were cut out from the normalized materials of 80 mm diameter, and the machining tests were performed with the NC lathe under the following machining conditions. The tool life was defined by the machining process time until the average amount of the side flank abrasion width of the tool became 200 μ m. Table 3 shows that the life ratio of the machined tool was defined by the value of the ratio when the value got in the comparative example 16 was 1.

Tool : Cemented carbide P10
Machining rate : 300 m/min
Feed : 0.2 mm/rev
Cutting : 2.0 mm
Cutting oil : Non

Rolling fatigue strength

[0035] Test pieces of 10 mm diameter x 20 mm length were cut out around the center axis of D/4 position of the normalized materials of 55 mm diameter, the induction quenching was performed at the frequency of 100 kHz and for the heating time of 3 seconds in the stationary type, then tempered 180°C x 60 min in the air, and subjected to the rolling fatigue tests.

[0036] The rolling fatigue tests were performed by the cylindrical rolling fatigue testing machine with the standard ball of SUJ2 made 3/4 inch steel ball and at the contact pressure of 5880 MPa. The rotation number was measured until injuries as pitting appeared on the face of the test piece, and made the life of the rolling fatigue, and the Weibull distribution curves were made from the lives of the rolling fatigue of 20 pieces of test pieces so as to demand the 10% breakage probability lives (L10). Table 3 shows that the value of the ratio when the 10% breakage probability life (L10) of the comparative material 16 was 1, was made the L10 life ratio. The gradients of the Weibull distribution curve were demanded, and the demanded values are shown as the parameter of dispersion in Table 3. Steels according to the present invention preferably have L10 life ratio as defined above of at least 2.0.

Torsion fatigue strength

[0037] Round bars of 20 mm diameter x 200 mm length were cut out from the normalized materials of 55 mm diameter, formed at 20 mm portions of both ends respectively with the splines of 20 mm pitch circle diameter and 1.0 module, subjected to the induction quenching at the frequency of 10 kHz so that the ratio of the hardened layer was 0.5, and was tempered 180°C x 60 min in the air to produce the torsion fatigue testing pieces.

[0038] The test pieces were fitted on the spline portions with holders, effected with torque, and performed with the torsion fatigue test so as to demand the strength for period of time of 2×10^5 times. The results are shown as the torsion fatigue strength in Table 3. Steels according to the present invention preferably have a torsion fatigue strength of at least

MPa determined as above.

Table 3-a

	Depth of hardened layer (mm)	Deformation resistance (MPa)	Ratios of lives of cold-worked tools	Ratios of lives of machined tools	Rolling fatigue strength		Torsion fatigue strength (MPa)
					L 10 lives	Parameters of dispersions	
Example 1	5.3	760	3.12	2.82	2.1	4.2	835
Example 2	5.3	784	2.76	2.51	3.2	4.6	845
Example 3	6.0	789	2.68	2.44	2.8	5.1	831
Example 4	5.7	795	2.39	2.20	3.2	4.8	843
Example 5	6.6	791	1.61	1.53	4.5	4.3	850
Example 6	5.9	774	2.55	2.33	4.8	4.9	855
Example 7	5.6	806	2.47	2.26	5.2	5.2	860
Example 8	0.2	821	2.22	2.05	5.6	4.5	871
Example 9	6.5	843	1.94	1.81	4.8	4.3	882
Example 10	6.0	824	1.94	1.81	6.2	5.2	851
Example 11	6.2	802	1.80	1.69	8.2	4.8	891
Example 12	5.9	818	1.88	1.75	9.4	4.7	887
Example 13	5.3	823	2.30	2.11	6.1	4.9	871
Example 14	5.4	832	2.12	1.96	4.9	5.0	873
Example 15	6.4	858	1.77	1.66	5.1	4.3	876

Table 3-b

	Depth of hardened layer (mm)	Deformation resistance (MPa)	Ratios of lives of cold-worked tools	Ratios of lives of machined tools	Rolling fatigue strength		Torsion fatigue strength (MPa)
					L10 lives	Parameters of dispersions	
Comparative example 1	5.1	724	3.59	3.22	0.1	4.5	791
Comparative example 2	7.1	913	1.31	1.27	2.1	4.7	851
Comparative example 3	7.2	899	1.25	1.21	3.1	4.5	871
Comparative example 4	3.5	774	2.95	2.68	0.7	4.6	792
Comparative example 5	3.3	780	2.99	2.71	0.8	4.4	772
Comparative example 6	6.5	831	2.10	1.94	0.9	2.6	821
Comparative example 7	5.2	804	2.56	2.34	0.7	2.4	805
Comparative example 8	5.7	807	2.50	2.29	0.8	2.5	810
Comparative example 9	5.0	843	1.98	1.85	1.3	2.8	814
Comparative example 10	5.6	800	2.50	2.30	1.0	2.7	802
Comparative example 11	5.7	807	2.35	2.29	1.1	2.5	810
Comparative example 12	5.6	798	2.20	2.12	0.9	2.6	799
Comparative example 13	5.7	802	2.12	2.10	2.3	4.2	785
Comparative example 14	5.9	865	1.73	1.63	6.1	4.0	781
Comparative example 15	4.9	879	1.53	1.45	0.5	3.2	702
Comparative example 16	5.2	918	1.00	1.00	1.0	3.4	802

[0039] According to the above tested results, in comparison with JIS S48C (Comparative example 15) and S53C (Comparative example 16) generally used for the induction quenching, the Comparative example 1 of lower C than the inventive range is superior in the cold workability but inferior in the rolling fatigue strength and the torsion fatigue

strength. The Comparative examples 2 and 3 of high Si and Mn are inferior in the cold workability. The Comparative examples 4 and 5 not containing B are inferior in the induction quenching and low in the rolling fatigue strength and the torsion fatigue strength.

5 [0040] The Comparative examples 6, 7 and 8 where the contents of O and N are high and large sized oxide based non-metallic inclusions and nitride based non-metallic inclusions are recognized, are lower in the rolling fatigue strength and the torsion fatigue strength and large in dispersion of the rolling fatigue strength. In the Comparative example 9 of high Ti, TiC is recognized in the metallic structure and the cold workability is inferior. The Comparative examples 10, 11 and 12 containing large sized non-metallic inclusions are low in the rolling fatigue strength and the torsion fatigue strength.

10 [0041] In the Comparative example 13 of low Al, the crystal grain is coarsened and the torsion fatigue strength is poor. The Comparative example 14 of high C is inferior in the cold workability and the torsion fatigue strength.

[0042] In contrast, it is seen that the Examples 1 to 15 of the invention have the excellent induction hardenability, cold workability, machinability, rolling fatigue strength and torsion fatigue strength. If using the inventive steels for the induction quenching, it is possible to provide the machinery structural parts having the superior rolling fatigue strength and torsion fatigue strength.

15 [0043] According to the invention, it is possible to offer steels suited to the induction quenching, having an excellent cold workability, high rolling fatigue strength and torsion fatigue strength with less dispersions of the fatigue strength as well as machinery structural parts.

[0044] Summarized, the present invention provides a steel product which contains, by mass%, C : 0.45 to 0.60%, Si : 0.01 to 0.15%, Mn : 0.20 to 0.60%, S : 0.012% or lower, Al : 0.015 to 0.040%, Ti 0.005 to 0.050%, B : 0.0005 to 0.0050%, N : 0.010% or lower, O : 0.0010% or lower, and balance being Fe and unavoidable impurities. Limitations are provided to allowable maximum sizes per each sort of contained non-metallic inclusions and the number per unit area thereof. This steel may contains one kind or two kinds or more of Cr: 1.00% or lower, Mo: 0.50% or lower and Ni: 1.50 or lower.

25 Claims

1. A steel for induction quenching comprising: by mass%,

30 C : 0.45 to 0.60%,
Si : 0.01 to 0.15%,
Mn : 0.20 to 0.60%,
S : 0.012% or lower,
Al : 0.015 to 0.040%,
35 Ti : 0.005 to 0.050%,
B : 0.0005 to 0.0050%,
N : 0.010% or lower,
O : 0.0010% or lower, and
balance being Fe and unavoidable impurities.

40 2. The steel for induction quenching according to claim 1 wherein maximum sizes of contained non-metallic inclusions are, in terms of equivalent circular diameters, 15 μm or less in oxide based non-metallic inclusions, 5 μm or less in nitride based non-metallic inclusions, and 15 μm or less in sulfide based non-metallic inclusions respectively, and the numbers of the non-metallic inclusions of the equivalent circular diameters being 1 μm or more are 6 or less per 1 mm^2 in the oxide based inclusions, 10 or less per 1 mm^2 in the nitride based non-metallic inclusions, and 5 or less per 1 mm^2 in the sulfide based non-metallic inclusions.

50 3. The steel for inductive quenching according to claim 2 wherein the numbers of oxide based non-metallic inclusions of the equivalent circular diameters being 1 μm or more are 5 or less.

4. The steel for induction quenching according to claim 2 or 3 wherein the sizes of nitride based non-metallic inclusions, in terms of equivalent circular diameters, are 4.5 μm or less.

55 5. The steel for induction quenching according to one of the preceding claims, further comprising, in addition to the above chemical composition, at least one of:

Cr: 1.00% or lower,
Mo: 0.50% or lower, and

Ni: 1.50% or lower.

- 5 6. The steel for induction quenching according to one of the preceding claims having a rolling fatigue strength, expressed as the ratio of the 10% breakage probability life to the 10% breakage probability life of steel JIS S53C, of at least 2.0.
7. The steel for induction quenching according to any one of the preceding claims, having of torsion fatigue strength of at least 800 MPa.
- 10 8. Machinery structural parts comprising the steel for induction quenching according to one of the previous claims.

15

20

25

30

35

40


45

50

55

107444) 1069201 A2 1069201 A2 1069201 A2

THIS PAGE BLANK (USPTO)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 069 201 A3**

(12) **EUROPEAN PATENT APPLICATION**

(88) Date of publication A3:
16.01.2002 Bulletin 2002/03

(51) Int Cl.7: **C22C 38/14, C22C 38/32**
// C21D1/10

(43) Date of publication A2:
17.01.2001 Bulletin 2001/03

(21) Application number: **00115224.8**

(22) Date of filing: **13.07.2000**

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: **13.07.1999 JP 19883699**

(71) Applicant: **DAIDO TOKUSHUKO KABUSHIKI**
KAISHA
Naka-ku Nagoya-shi Aichi-ken (JP)

(72) Inventors:
• **Matsumura, Yasushi, c/o Daido Tokushuko K.K.**
Nagoya-shi, Aichi (JP)
• **Kurebayashi, Yutaka, c/o Daido Tokushuko K.K.**
Nagoya-shi, Aichi (JP)
• **Nakamura, Sadayuki, c/o Daido Tokushuko K.K.**
Nagoya-shi, Aichi (JP)

(74) Representative:
Diehl, Hermann, Dr. Dipl.-Phys. et al
DIEHL, GLÄSER, HILTL & PARTNER
Patentanwälte Augustenstrasse 46
80333 München (DE)

(54) **Steel for induction hardening**

(57) A steel product contains, by mass%, C : 0.45 to 0.60%, Si : 0.01 to 0.15%, Mn : 0.20 to 0.60%, S : 0.012% or lower, Al : 0.015 to 0.040%, Ti : 0.005 to 0.050%, B : 0.0005 to 0.0050%, N : 0.010% or lower, O : 0.0010% or lower, and balance being Fe and una-

voidable impurities. Limitations are provided to allowable maximum sizes per each sort of contained non-metallic inclusions and the number per unit area thereof. This steel may contains one kind or two kinds or more of Cr: 1.00% or lower, Mo: 0.50% or lower and Ni: 1.50 or lower.

EP 1 069 201 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 11 5224

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	PATENT ABSTRACTS OF JAPAN vol. 017, no. 373 (C-1083), 14 July 1993 (1993-07-14) -& JP 05 059486 A (KOBE STEEL LTD), 9 March 1993 (1993-03-09) * abstract * * page 4; examples 3,4,8,10,11,13,14,17,19-24; table 1 *	1-8	C22C38/14 C22C38/32 //C21D1/10
X	PATENT ABSTRACTS OF JAPAN vol. 1999, no. 08, 30 June 1999 (1999-06-30) -& JP 11 071630 A (SANYO SPECIAL STEEL CO LTD), 16 March 1999 (1999-03-16) * abstract * * page 4; example 5; table 1 *	1-8	
X	PATENT ABSTRACTS OF JAPAN vol. 1998, no. 14, 31 December 1998 (1998-12-31) -& JP 10 251806 A (SANYO SPECIAL STEEL CO LTD), 22 September 1998 (1998-09-22) * abstract * * page 4; example 5; table 1 *	1-8	TECHNICAL FIELDS SEARCHED (Int.Cl.7) C22C
X	PATENT ABSTRACTS OF JAPAN vol. 1997, no. 07, 31 July 1997 (1997-07-31) -& JP 09 078127 A (DAIDO STEEL CO LTD), 25 March 1997 (1997-03-25) * abstract * * page 4; example 7; table 1 *	1-8	
		-/--	
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 26 November 2001	Examiner Patton, G
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPO FORM 1503 03-82 (P04C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 11 5224

DOCUMENTS CONSIDERED TO BE RELEVANT				
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)	
X	PATENT ABSTRACTS OF JAPAN vol. 1998, no. 12, 31 October 1998 (1998-10-31) -& JP 10 195589 A (NIPPON STEEL CORP), 28 July 1998 (1998-07-28) * abstract * * page 8; examples 5,17; table 1 * * page 11; example 7; table 2 * * page 12; examples 3,6; table 3 * * page 15; example 1; table 5 * * page 16; example 1; table 6 *	1-8		
X,D	PATENT ABSTRACTS OF JAPAN vol. 014, no. 356 (C-0745), 2 August 1990 (1990-08-02) -& JP 02 129341 A (KAWASAKI STEEL CORP), 17 May 1990 (1990-05-17) * abstract * * page 4; examples 6,9; table 1 *	1-8		
P,X	GB 2 345 116 A (HONDA MOTOR CO LTD) 28 June 2000 (2000-06-28) * page 2, line 27 - page 3, line 14 * * page 12; examples 4,5; table 1 *	1-8		TECHNICAL FIELDS SEARCHED (Int.Cl.7)
E	WO 01 02615 A (NIPPON STEEL CORP ;ADACHI KOJI (JP); KUBOTA MANABU (JP); KANISAWA) 11 January 2001 (2001-01-11) * page 4, line 10 - page 6, line 19 * * page 18; example D; table 1 * * claims *	1-8		
E	US 6 123 785 A (IGUCHI MAKOTO ET AL) 26 September 2000 (2000-09-26) * column 1, line 39 - column 3, line 59 * * examples 1-3,7,9; table 1 *	1-8		
The present search report has been drawn up for all claims				
Place of search MUNICH		Date of completion of the search 26 November 2001	Examiner Patton, G	
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document		

EPO FORM 1503 03.02 (PatCat)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 11 5224

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

26-11-2001

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
JP 05059486	A	09-03-1993	NONE		
JP 11071630	A	16-03-1999	NONE		
JP 10251806	A	22-09-1998	NONE		
JP 09078127	A	25-03-1997	NONE		
JP 10195589	A	28-07-1998	NONE		
JP 02129341	A	17-05-1990	JP	2610662 B2	14-05-1997
GB 2345116	A	28-06-2000	JP	2000154828 A	06-06-2000
			DE	19955385 A1	20-07-2000
WO 0102615	A	11-01-2001	JP	2001011575 A	16-01-2001
			CN	1316018 T	03-10-2001
			EP	1119648 A1	01-08-2001
			WO	0102615 A1	11-01-2001
US 6123785	A	26-09-2000	DE	19950264 A1	19-04-2001
			GB	2355271 A	18-04-2001

EPO FORM P4439

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82